

AERO final lacquer 50 610 glossy 50 611 matt 50 612 soft-touch

product name:

- AERO final lacquer glossy / matt / soft-touch.

ingredients:

- Polyurethane-/ polyacrylate dispersion, water. 50611 and 50612 also contains additives like matting agents.

basic information:

- Final lacquers for working with AERO COLOR® Professional.

characteristics:

- Glossy (50610) / matt (50611) / soft-touch (50612)
- colourless and transparent
- flexible
- elastic
- scratch-resistant
- light-resistant and non-aging.

handling:

- Shake well before use.
- AERO final lacquer glossy / matt / soft-touch is water-mixable, but dries up to a water-insoluble film (hardening: 48 h).
- Apply first layer very thin/"dry". After a ventilation time from approx. 10 min. apply a second layer in a more rich/"wet" way to get a sealed surface.
- Please clean tools as soon as possible with water and/or AERO CLEAN RAPID 50606.
- Best results are achieved with spray application at processing temperatures between 15 and 30 °C, 2 bar air pressure and a nozzle size of > 0,3 mm.
- Please don't use the product below temperatures under 10 °C object- and room-temperatures.
- Close immediately after use.
- Store in a cool and dry place.
- Protect from frost.
- Individual pre-tests are required (see footer).

product labeling:

- Please refer to the individual safety data sheet on our website www.schmincke.de or www.aerocolor.de.

DrK/ 01.07.2014



H. Schmincke & Co. GmbH & Co. KG · Otto-Hahn-Str. 2 · D - 40699 Erkrath ·
Tel.: +49-211-2509-0 · www.schmincke.de · info@schmincke.de

The described product characteristics and example applications have been tested at the Schmincke laboratory. The information is based on the technical knowledge and experience which are presently available to us. In view of the diversity of applications with regard to painting techniques, materials and working conditions and the numerous possible influencing factors, the information refers to general areas of application. The information provided here does not constitute a legally binding warranty of specific characteristics or of suitability for a specific application; use of the products is thus to be adapted to the user's special conditions and checked by preliminary tests. We are thus unable to guarantee product characteristics or accept any liability for damage arising in connection with the use of our products.